



PP 2000

Product Information

The PP 2000 is a polypropylene created with the specific intention to be used for rotational molding

General Information

Material Status	- Commercial: Active
Availability	- North America
Additive	- UV Stabilizer: Yes
Appearance	- Natural Color
Forms	- Pellets and Powder
Processing Method	- Rotational Molding

Physical Information

English Unit

Test Method

Melt Index	15.0G/10 MIN	ASTM D-1238
Density	.90G/CC	ASTM D-1505
Tensile .125" Thick	4,000 PSI	ASTM D-638
Flexural Modulus 1% Strain	175,000 PSI	ASTM D-790
Arm Cold (-40°F) Temperature Impact 0.125" Specimen	10 FT/LB.	ARM METHOD
Deflection Temperature Under Load 66PSI (0.45 MPa)	245°F	ASTM D-648

FOR YOUR PROTECTION

THE INFORMATION AND RECOMMENDATIONS IN THIS PUBLICATION ARE TO THE BEST OF OUR KNOWLEDGE AND ARE RELIABLE. SUGGESTIONS CONCERNING USES OR APPLICATIONS ARE ONLY THE OPINION OF JERICO PLASTIC INDUSTRIES, INC. AND USERS SHOULD MAKE THEIR OWN TESTS TO DETERMINE THE SUITABILITY OF THIS PRODUCT FOR THEIR PARTICULAR PURPOSES. HOWEVER, BECAUSE OF NUMEROUS FACTORS AFFECTING RESULTS, JERICO PLASTIC INDUSTRIES, INC. MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED. INCLUDING THOSE OF MERCHANTABILITY AND FITNESS PURPOSES OTHER THAN THAT THE MATERIAL CONFORMS TO ITS APPLICABLE CURRENT STANDARD SPECIFICATIONS. STATEMENTS HEREIN SHOULD NOT BE CONSTRUED AS REPRESENTATIONS OF WARRANTIES. THE RESPONSIBILITY OF JERICO PLASTIC INDUSTRIES, INC FOR CLAIMS ARISING OUT OF BREACH WARRANTY, NEGLIGENCE, STRICT LIABILITY, OR OTHERWISE IS LIMITED TO THE PURCHASE PRICE OF THE MATERIAL.