



Jerico Plastic Industries, Inc.

SL 9437

Product Information

The SL 9437 has excellent impact with good stiffness. This product is UV stabilized, FDA compliance is available, and available in multi mesh powder as well as 35 mesh powder.

General Information

| | |
|-------------------|--|
| Material Status | Commercial: Active |
| Availability | FDA Available and Multi Mesh Available |
| Additive | UV Stabilized |
| Appearance | Colors |
| Forms | Pellets and Powder |
| Processing Method | Rotational Molding |

Physical Information

English Unit

Test Method

| | <u>English Unit</u> | <u>Test Method</u> |
|---|---------------------|--------------------|
| Melt Index | 7.0G/10 MIN | ASTM D-1238 |
| Density | .943G/CC | ASTM D-1505 |
| Tensile .125" Thick | 2,750 PSI | ASTM D-638 |
| Flexural Modulus 1% Strain | 108,000 PSI | ASTM D-790 |
| Arm Cold (-40°F) Temperature Impact 0.125" Specimen | 55 FTL/LB | ARM METHOD |
| Ultimate Elongation | 300 | * |

FOR YOUR PROTECTION

THE INFORMATION AND RECOMMENDATIONS IN THIS PUBLICATION ARE TO THE BEST OF OUR KNOWLEDGE AND ARE RELIABLE. SUGGESTIONS CONCERNING USES OR APPLICATIONS ARE ONLY THE OPINION OF JERICO PLASTIC INDUSTRIES, INC. AND USERS SHOULD MAKE THEIR OWN TESTS TO DETERMINE THE SUITABILITY OF THIS PRODUCT FOR THEIR PARTICULAR PURPOSES. HOWEVER, BECAUSE OF NUMEROUS FACTORS AFFECTING RESULTS, JERICO PLASTIC INDUSTRIES, INC. MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED. INCLUDING THOSE OF MERCHANTABILITY AND FITNESS PURPOSES OTHER THAN THAT THE MATERIAL CONFORMS TO ITS APPLICABLE CURRENT STANDARD SPECIFICATIONS. STATEMENTS HEREIN SHOULD NOT BE CONSTRUED AS REPRESENTATIONS OF WARRANTIES. THE RESPONSIBILITY OF JERICO PLASTIC INDUSTRIES, INC FOR CLAIMS ARISING OUT OF BREACH WARRANTY, NEGLIGENCE, STRICT LIABILITY, OR OTHERWISE IS LIMITED TO THE PURCHASE PRICE OF THE MATERIAL.